

# VETRONITE EGS 619 HTC

HIGH THERMAL CONDUCTIVITY GLASS-FABRIC EPOXY COMPOSITE

## APPLICATION

- + **Electrical insulating** and **heat dissipating material** for **electro-technical equipment**
- + Applications comprise **medical equipment** like **MRI** and **CT scanners**

## BENEFITS

- + **Strong** composite laminate made of **glass cloth** and **high temperature epoxy** with **thermal conductive filler**
- + **Outstanding thermal conductivity**
- + **Excellent mechanical** and **electrical properties**
- + **Flame retardant** acc. to **UL 94, class V-0**



	Unit	Value
<b>Mechanical properties</b>		
Flexural strength	MPa (psi)	450 (65,300)
E-modulus	MPa (Mpsi)	24.000 (3.5)
Compressive strength //, at 23°C	MPa (psi)	250 (36,300)
Compressive strength ⊥, at 23°C	MPa (psi)	420 (60,900)
Tensile strength	MPa (psi)	300 (43,500)
<b>Thermal properties</b>		
Temperature index (TI)	°C	130 (Class B)
Thermal conductivity (ISO 8301)	W/mK (Btu/foot h °F)	0.86 (0.5)

	Unit	Value
<b>Electrical properties</b>		
Insulation resistance	Ohm	10 <sup>12</sup>
Breakdown voltage //, 90°C in oil	kV	65
Electric strength ⊥, 90°C in oil	kV/mm	15
Comparative tracking index CTI		300
Relative permittivity at 1 MHz		5.3
Dissipation factor at 1 MHz		0.01
<b>Physical properties</b>		
Density	g/cm <sup>3</sup> (lb/ft <sup>3</sup> )	2.05 (128)

**Sheet sizes** 1270 × 1070mm (50in × 42in), 1170 × 1070mm (46in × 42in) (others on request)

**Thickness range** 0.2 to 50 mm (8 to 2000 mils)

## VALUE PROPOSITION

- + Record of many customers successfully using Vetronite EGS 619 HTC for many years for specific applications in medical technology
- + Von Roll's decade long experience in composite manufacturing combined with state-of-the-art production facilities lead to high quality products



# CONTACT US:

## EUROPE

Von Roll Schweiz AG  
Passwangstrasse 20  
4426 Breitenbach  
Switzerland  
+41 61 785 51 11  
cs.europe.mica@vonroll.com

Von Roll Italia S.r.l.  
Via Rigolfo, n° 73 (zona Vadò)  
10028 Trofarello (TO)  
Italy  
+39 011 649 31 11  
cs.europe.liqu@vonroll.com

Von Roll France SA  
145, rue de la République,  
BP 128  
69883 Meyzieu Cedex  
France  
+33 478 045 904  
cs.europe.liqu@vonroll.com

Von Roll Deutschland GmbH  
Theodor-Sachs-Straße 1  
86199 Augsburg  
+49 0821 90 20  
cs.europe.comp@vonroll.com

Von Roll UK Ltd.  
42 Wharfedale Road,  
Euroway Estate  
West Yorkshire BD4 6SG Bradford  
United Kingdom  
+44 1274 68 77 77  
cs.europe.comp@vonroll.com

## AMERICA

Von Roll USA, Inc.  
200 Von Roll Drive  
Schenectady, NY 12306  
USA  
+1 518 344 71 00  
sales.us@vonroll.com

## ASIA/PACIFIC

Von Roll do Brasil Ltda.  
Avenida Parque Central s/n,  
Distrito Industrial  
61939-140 Maracanaú, CE  
Brazil  
+55 85 400 848 84  
cs.south.america@vonroll.com

Von Roll Asia Pte Ltd.  
Woods Square, Tower 2  
6 Woodlands Square #08-06  
Singapore 737737  
Singapore  
+65 655 647 88  
cs.asia@vonroll.com

Von Roll Shanghai Co., Ltd.  
Unit C, No.1235, Minqiang Road  
Songjiang District  
Shanghai, 201612  
China  
+86 21 676 870 20  
cs.asia@vonroll.com

Von Roll India Pvt Ltd.  
15/1/2, 20/1B,  
Kempalinganahalli  
NH-48, Kunigal Road,  
Nelamangala  
Bangalore-562123  
India  
+91 80 230 877 00  
cs.india@vonroll.com

The logo for vonRoll, featuring the word 'vonRoll' in a bold, dark blue, sans-serif font. The 'v' is lowercase and the 'o' is lowercase, while 'nRoll' is uppercase.